



(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 704 093 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
18.03.1998 Bulletin 1998/12

(51) Int Cl. 6: **G21K 1/00, G21C 5/00,**
A61N 5/10

(21) Application number: **94915579.0**

(86) International application number:
PCT/FI94/00206

(22) Date of filing: **24.05.1994**

(87) International publication number:
WO 94/29881 (22.12.1994 Gazette 1994/28)

(54) MODERATOR MATERIAL FOR NEUTRONS AND USE OF SAID MATERIAL

NEUTRONENMODERATORMATERIAL UND SEINE VERWENDUNG

MATERIAU MODERATEUR DE NEUTRONS ET SON UTILISATION

(84) Designated Contracting States:
AT BE CH DE DK ES FR GB GR IE IT LI LU NL PT
SE
Designated Extension States:
SI

(30) Priority: **14.06.1993 FI 932711**

(43) Date of publication of application:
03.04.1996 Bulletin 1996/14

(73) Proprietor: **VALTION TEKNILLINEN**
TUTKIMUSKESKUS
02150 Espoo (FI)

(72) Inventors:
• **HIISMÄKI, Pekka**
FIN-02320 Espoo (FI)
• **AUTERINEN, Iiro**
FIN-00530 Helsinki (FI)

(74) Representative: **Rostovanyi, Peter et al**
AWAPATENT AB,
Box 5117
200 71 Malmö (SE)

(56) References cited:
FR-A- 2 262 379 **US-A- 4 566 989**
US-A- 4 675 150 **US-A- 5 015 863**

EP 0 704 093 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description


The invention concerns a moderator material used for moderation of high-velocity neutrons, in particular of fission neutrons, to epithermal neutrons.

Further, the invention concerns a novel use of the moderator material for neutrons in accordance with the invention.

With respect to the prior art related to the present invention, reference is made to the cited paper *Proceedings of an International Workshop on Neutron Beam Design, Development, and Performance for Neutron Capture Therapy*, held March 29-31, 1989, at the Massachusetts Institute of Technology, in Cambridge, Massachusetts, Edited by Otto K. Harling, John A. Bernard and Robert G. Zamenhof, Plenum Press, New York.

The boron neutron capture therapy (BNCT) is based thereon that, to the patient, through the blood circulation, an agent is administered that seeks its way into the cancer tissue and to whose molecule components have been attached that include boron atoms. A neutron flux is directed at the location of the cancer tissue, the neutrons in said neutron flux being absorbed into the boron and splitting the boron to lithium and helium, which destroy exactly cancer cells very locally, but which destroy any other tissue very little.

In BNCT, the formula of the boron neutron capture is as follows:



The boron neutron capture therapy produces quite a little strain on the patient. Surgical operation and anaesthesia are not needed. For the therapy team, the radiation strain does not differ in any way from administration of conventional radiological therapy.

In BNCT, slow or thermal neutrons have been used, whose depth of penetration is so little that the patient's cranium must be opened for the time of the therapy. On the contrary, epithermal neutrons of higher velocity are not moderated for capture by boron atoms until in the interior of the head, in which case the cranium does not have to be opened.

In boron neutron capture therapy, attempts are made to produce a distribution of the flux of thermal neutrons in the area of the body part to be treated, for example the head, which distribution of flux has a rather wide maximum sufficiently deep in the area to be treated. It is well known that this aim is reached best if epithermal neutrons are passed from an external source to the body part to be treated, which neutrons are not thermalized until in the interior of the body. The neutron source best suitable for the therapy purpose is a re-

search reactor, which produces primarily high-velocity fission neutrons. They must be moderated under control to epithermal neutrons, to the energy range of 1 eV...10 keV, so that the proportion of high-velocity neutrons remains sufficiently low. As is known from prior art, many different materials have been suggested for the moderator material, such as metallic aluminum, aluminum oxide, aluminum fluoride, silicon, and equivalent.

5 Aluminum fluoride is a subliming compound, which is available as a porous powder, but out of it, it is impossible to prepare a dense material free of pores. Porosity is a drawback in principle, for it increases the necessary material thickness and brings the treatment point unduly far from the primary source, thereby lowering the useful intensity that can be achieved.

10 The object of the present invention is to provide a novel moderator material for neutrons by which means the above drawbacks can be eliminated.

15 In view of achieving the objectives stated above and those that will come out later, the moderator material in accordance with the invention is mainly characterized in that the principal components of the moderator material are aluminum fluoride and aluminum metal, which have been formed into a dense composite substantially free of pores.

20 According to the present invention, the moderator material defined above is used in boron neutron capture therapy (BNCT) of cancer tissues.

25 In the following, the invention will be described in detail with reference to the schematic illustration in the accompanying drawing, which is an illustration of principle of BNCT therapy by means of a research reactor.

30 In the figure, a research reactor is shown as used in BNCT therapy. In a way in itself known, the reactor comprises a reactor core 10, a graphite reflector 11 surrounding said core, and a tank 12 with aluminum walls, which tank is filled with water. The BNCT station is constructed by replacing the graphite, which is placed around the reactor core 10 in a so-called thermal column, with a moderator material piece 15, which requires an epithermal beam and which is made of the material in accordance with the present invention, and with a gamma shield 13. The patient P, in whose head H the cancer tumour to be irradiated is placed, is surrounded 35 by a lead shield 14 and by a deuterium/lithium epithermal-thermal neutron shield 17. The concrete frame of the reactor is denoted with the reference numeral 16. In order that the patient P could be placed in the neutron beam as freely as possible, the thermal column is widened in the horizontal direction by cutting the concrete wall of the reactor thinner. The radiation space R is lined with a gamma and neutron shield and isolated from the reactor hall by means of boronized heavy-concrete units.

40 45 50 55 According to calculations that have been made, an optimal moderator material for the moderator piece 15 is a material in which the atomic ratio of aluminum to fluorine is clearly higher than that in aluminum fluoride

1:3. This goal is achieved by preparing a composite in which the pores in aluminum fluoride are filled with aluminum metal. The manufacture of the composite is carried out, for example, by means of the so-called HIP technique (HIP = hot isostatic pressing). If necessary, to the material, it is possible to add little amounts of a substance that absorbs thermal neutrons, such as lithium, for example in the form of lithium fluoride, if it is desirable to get rid of the component of thermal neutrons without formation of an intensive capture gamma source at the same time.

In a moderator material in accordance with the invention, the amount of aluminum is preferably 20...50 %-vol. (per cent by volume) and that of aluminum fluoride 80...50 %-vol. With the above range of mixing ratio of aluminum to aluminum fluoride, in the moderator piece 15, out of the metallic aluminum, a unified and continuous, three-dimensionally network-formed matrix is formed, which keeps the moderator piece 15 together and in which the interior spaces are completely and densely filled with aluminum fluoride. The amount of lithium fluoride, which absorbs thermal neutrons, is preferably about 1 %.-vol.

A moderator piece 15 that is made of a material in accordance with the invention has typically the dimensions 700 x 1000 x 1000 mm, of which the dimension L₂ indicated in the figure is L₂ ≈ 700 mm. The dimensions L₁ and L₃ indicated in the figure are typically L₁ ≈ 1050 mm and L₃ ≈ 100 mm.

In the following, the patent claims will be given, and the various details of the invention may show variation within the scope of the inventive idea defined in said claims and differ from what has been stated above by way of example only.

Claims

1. Moderator material used for moderation of high-velocity neutrons, in particular of fission neutrons, to epithermal neutrons, **characterized** in that the principal components of the moderator material are aluminum fluoride and aluminum metal, which have been formed into a dense composite substantially free of pores.
2. Moderator material as claimed in claim 1, **characterized** in that the material contains 20...50 %-vol. of aluminum metal and 80...50 %-vol. of aluminum fluoride.
3. Moderator material as claimed in claim 2, **characterized** in that, into a moderator piece (15) that is made of the moderator material, out of the aluminum metal, a continuous, three-dimensional, network-formed matrix is formed, in whose interior the remaining spaces are filled by aluminum fluoride substantially completely.

4. Moderator material as claimed in any of the claims 1 to 3, **characterized** in that, to the moderator material, a substance which absorbs thermal neutrons has been added, such as lithium fluoride, which does not produce high-energy gamma rays that are difficult to attenuate.
5. Moderator material as claimed in claim 4, **characterized** in that lithium fluoride has been added to the moderator material as an amount of about 1 %-vol.
6. The use of the moderator material as claimed in any of the claims 1 to 5 in neutron capture therapy of cancer tumours.
7. The use as claimed in claim 6 in boron neutron capture therapy (BNCT).
8. The use of the moderator material as claimed in any of the claims 1 to 5, wherein epithermal neutrons are passed from an external source into the body part (H) to be treated, which neutrons are not thermalized until in the interior of the body.
9. The use as claimed in any of the claims 6 to 8, wherein the neutron source is a research reactor, which produces primarily high-velocity fission neutrons, which are moderated under control to epithermal neutrons to the energy range of 1 eV...10 keV, so that the proportion of high-velocity neutrons remains sufficiently low.

Patentansprüche

1. Moderatormaterial zur Moderierung von Hochgeschwindigkeitsneutronen, insbesondere von Spaltneutronen, zu epithermischen Neutronen, **dadurch gekennzeichnet**, daß die Hauptkomponenten des Moderatormaterials Aluminiumfluorid und Aluminium-Metall sind, die in ein dichtes, im wesentlichen porenfreies Komposit geformt sind.
2. Moderatormaterial nach Anspruch 1, **dadurch gekennzeichnet**, daß das Material 20 bis 50 Vol-% Aluminium-Metall und 80 bis 50 Vol-% Aluminiumfluorid enthält.
3. Moderatormaterial nach Anspruch 2, **dadurch gekennzeichnet**, daß in ein Moderatorstück (15), welches aus dem Moderatormaterial hergestellt ist, eine kontinuierliche, dreidimensionale netzförmige Matrix aus dem Aluminium-Metall eingefügt ist, in deren Innerem die verbleibenden Räume im wesentlichen vollständig mit Aluminiumfluorid ausgefüllt sind.

Revendications

- 40

 1. Matériau modérateur utilisé pour la modération de neutrons à grande vitesse, en particulier les neutrons de fission, en neutrons épithermiques, caractérisé en ce que les principaux composants du matériau modérateur sont le fluorure d'aluminium et le métal d'aluminium qui ont été formés en un composite dense, sensiblement exempt de pores.
 2. Matériau modérateur selon la revendication 1, caractérisé en ce que le matériau contient 20.... 50 % en volume de métal d'aluminium et 80.... 50 % en volume de fluorure d'aluminium.
 3. Matériau modérateur selon la revendication 2, caractérisé en ce que dans un élément modérateur (15) qui est réalisé à partir du matériau modérateur, en métal d'aluminium, on forme une matrice continue tridimensionnelle réticulaire, à l'intérieur de la

45

50

55

